

---

<b>Type</b>	Un saturated polyester resin based on Isophthalic acid
<b>Description</b>	C'POL 3311 is a medium reactivity, useful for the fabrication of a wide range of hand moulded FRP structures for Chemical Industry, Structures made with C'POL- 3311 possess excellent resistance to water and host of corrosive chemicals such as dilute acids and salt solutions.

---

\*\* To obtain the Technical Data Sheet (TDS) of the product, please mail us at [enquiry@crestresins.com](mailto:enquiry@crestresins.com).

This information and our technical advice – whether verbal, in writing or by way of trials – are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided – especially that contained in our safety data and technical information sheets – and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale & Delivery. This does not apply to Trail-Products.