

Rev :05

Type	Fire Retardant Unsaturated Polyester Resin
Description	C'POL 16113 is pre-accelerated, thixotropic, Fire Retardant Orthophthalic resin designed to offer the maximum degree of Limiting Oxygen Index, Low Smoke Density. It has excellent chemical resistance and toughness.

Specifications

Property	Value	Unit of Measurement
Viscosity @ 25°C (RV,Spindle-2,Rpm-20)	1000 ± 200	mPa.s
Specific Gravity @ 25°C	1.47 ± 0.03	gms / cc
Gel Time @ 25°C (with 1.5% MEKP)	10-20	minutes

These properties are tested for liquid resin in accordance with the methods described in IS 6746 - 1994

Mechanical Properties (cast resin)

Property	Value	Unit of Measurement
Tensile Strength	30	Mpa
Tensile Modulus	5400	Mpa
Flexural Strength	55	Mpa
Flexural Modulus	3600	Mpa
Elongation at Break	1.13	%
Heat Distortion Temperature	85	°C

Cast cured for 24 hrs. At room temperature followed by 6 hrs. At 110 °C

Crest Speciality Resins Pvt. Ltd

C'POL 16113

Technical Data Sheet

Rev :00

Properties/Applications

This resin is useful in hand lay up & spray up applications where excellent fire retardant properties like Low Smoke Density, Oxygen Index, Flame spread along with mechanical strength is required.

Storage

Store below 25 °C & low humidity in securely closed containers. Exposure of containers to direct sunlight should be avoided at all cost. If proper storage facility is not available please consume the material as soon as it is delivered. Storage at high temperatures will adversely affect the shelf life.

Shelf life

If stored at suggested conditions the material is guaranteed 2 month(s) shelf life from the date of manufacturing. Opening the container to allow fresh air and rolling the can can help in improving the shelf life.

Safety

Hazards Identification

Repeated exposure may cause skin dryness or cracking. Vapors may cause drowsiness and dizziness. The safety data sheet should be observed. This contains information on labeling, transport and storage as well as on handling, product safety and ecology.

This information and our technical advice – whether verbal, in writing or by way of trials – are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided – especially that contained in our safety data and technical information sheets – and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale & Delivery. This Does not apply to Trial –Products.